

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings of claims in the application:

LISTING OF CLAIMS:

1. - 26. (cancelled)

27. (currently amended) A method of producing a porous plastic film, the method comprising:

producing a stretchable preform from a raw material blend comprising a polymer-containing basic material and an additive [[,]];

stretching the ~~blank~~ preform so as to form a film comprising pores [[,]]; and

charging the porous film by directing an electric field over [[it]] the porous film, wherein,

the additive ~~comprising~~ comprises a POS(S) chemical, and

at least part of the POS(S) chemical is in agglomerates.

28. (previously presented) A method as claimed in claim 27, wherein the preform is stretched biaxially.

29. (currently amended) A method as claimed in claim

27, ~~stretching the preform~~ wherein the preform is stretched
within a draw ratio range of 2:1 to 8:1.

30. (previously presented) A method as claimed in claim
27, wherein the POS(S) is in a solid state at room temperature.

31. (previously presented) A method as claimed in
claim 30, wherein the POS(S) is blended with the basic material
at a temperature lower than the melting temperature of the
POS(S).

32. (previously presented) A method as claimed in
claim 30, wherein the POS(S) is blended with the basic material
at a temperature exceeding the melting temperature of the POS(S).

33. (previously presented) A method as claimed in claim
27, wherein the POS(S) is in a liquid state at room temperature.

34. (currently amended) A method as claimed in claim
27, wherein the POS(S) comprises one or more of the following
chemicals: dodecaphenyl-POSS $C_{17}H_{60}O_{18}Si_{12}$, isooctyl-POSS
 ~~$[Me_3CCH_2CH(Me)CH_2]_nT_n$~~ $[Me_3CCH_2CH(Me)CH_2]_n(SiO_{1.5})_n$, wherein $n = 8, 10$
or 12 , octacyclohexyl-POSS $C_{48}H_{88}O_{12}Si_8$, octacyclopentyl-POSS
 $C_{40}H_{72}O_{12}Si_8$, octaisobutyl-POSS $C_{32}H_{72}O_{12}Si_8$, octamethyl-POSS
 $C_8H_{24}O_{12}Si_8$, octaphenyl-POSS $C_{48}H_{40}O_{12}Si_8$, octa-TMA-POSS

$C_{32}H_{96}O_{20}Si_8 \cdot \sim 60 H_2O$, dodecatrifluoropropyl-POSS $C_{36}H_{48}F_{36}O_{18}Si_{12}$, octatrimethylsiloxo-POSS $C_{24}H_{72}O_{20}Si_{16}$, phenetyl-POSS $(PhCH_2CH_2)_nT_n$ $(PhCH_2CH_2)_n(SiO_{1.5})_n$, wherein $n = 8, 10$ or 12 , phenetylisobutyl-POSS $C_{36}H_{72}O_{12}Si_8$.

35. (currently amended) A method as claimed in claim 27, wherein the basic material comprises one or more of the following polymers: polypropylenes, cyclic olefin copolymers, cyclic olefin polymers, polymethylpentene, polyethylene terephthalate, polybutene terephthalate, polyethylene naphthalate, polyeterimide polyetherimide.

36. (previously presented) A method as claimed in claim 27, wherein the thickness of the porous plastic film is 5 to 200 μm .

37. (previously presented) A method as claimed in claim 27, wherein the amount of POS(S) is 0.1 to 50 percent by weight calculated from the weight of the basic material.

38. (previously presented) A method as claimed in claim 27, wherein the pores comprised by the film are expanded with gas.

39. (currently amended) A method as claimed in claim 27, wherein an electrically conductive element is prepared on at ~~lest~~ least one side of the porous film.

40. (currently amended) A porous plastic film produced from a raw material blend ~~containing~~ comprising:

a basic material and an additive mixed therewith[[,]]; and

a plurality of pores being arranged in the structure of the plastic film, the pores being produced by stretching a preform made from the raw material blend; and

~~the plastic film being electrically charged~~ an electrical charge, wherein,

the additive ~~comprising~~ comprises a POS(S) chemical, and

at least part of the POS(S) chemical is in agglomerates.

41. (previously presented) A plastic film as claimed in claim 40, wherein the pores are produced by stretching the preform biaxially.

42. (previously presented) A plastic film as claimed in claim 40, wherein the draw ratio of the stretching is within a draw ratio range of 2:1 to 8:1.

43. (previously presented) A plastic film as claimed in claim 40, wherein the pores are closed pores.

44. (currently amended) A plastic film as claimed in claim 40, wherein the POS(S) comprises one or more of the following chemicals: dodecaphenyl-POSS $C_{17}H_{60}O_{18}Si_{12}$, isooctyl-POSS $[Me_3CCH_2CH(Me)CH_2]_nT_n$ $[Me_3CCH_2CH(Me)CH_2]_n(SiO_{1.5})_n$, wherein $n = 8, 10$ or 12 , octacyclohexyl-POSS $C_{48}H_{88}O_{12}Si_8$, octacyclopentyl-POSS $C_{40}H_{72}O_{12}Si_8$, octaisobutyl-POSS $C_{32}H_{72}O_{12}Si_8$, octamethyl-POSS $C_8H_{24}O_{12}Si_8$, octaphenyl-POSS $C_{48}H_{40}O_{12}Si_8$, octa-TMA-POSS $C_{32}H_{96}O_{20}Si_8 \cdot \sim 60 H_2O$, dodecatrifluoropropyl-POSS $C_{36}H_{48}F_{36}O_{18}Si_{12}$, octatrimethylsiloxy-POSS $C_{24}H_{72}O_{20}Si_{16}$, phenetyl-POSS $(PhCH_2CH_2)_nT_n$ $(PhCH_2CH_2)_n(SiO_{1.5})_n$, wherein $n = 8, 10$ or 12 , phenetylisobutyl-POSS $C_{36}H_{72}O_{12}Si_8$.

45. (currently amended) A plastic film as claimed in claim 40, wherein the basic material comprises one or more of the following polymers: polypropylenes, cyclic olefin copolymers, cyclic olefin polymers, polymethylpentene, polyethylene terephthalate, polybutene terephthalate, polyethylene naphthalate, polyeterimide polyetherimide.

46. (previously presented) A plastic film as claimed in claim 40, wherein at least one of its surfaces is at least

partly coated with an electrically conductive coating.

47. (previously presented) A plastic film as claimed in claim 40, wherein it is an electromechanical film and/or an electret film.

48. (previously presented) A plastic film as claimed in claim 47, wherein a change in electromechanical energy is arranged to take place through a change in the thickness of the film.

49. (previously presented) A plastic film as claimed in claim 47, wherein a change in electromechanical energy is based on variation of the location of the film in an electric field.